



System Reference	Surface Area and Conditions	Coating System	Surface Preparation	Typical Dry Film Thickness	
				Microns	Mils
TANK LININGS					
T-25	Water, Fire Water NOTE: For locally approved potable water linings, consult PPG Technical Service.	Amerlock Series High-solids Epoxy Amerlock Series High-solids Epoxy Amerlock Series High-solids Epoxy	SSPC-SP10 (Sa 2 1/2)	125 - 150 stripe coat 125 - 150 250 - 300	5 - 6 5 - 6 10 - 12
T-26	Storage Tanks [Check the PPG Protective and Marine Coatings Chemical Resistance List for particular storage content or consult PPG Technical Service for a recommendation]	Amercoat 90 Series Phenolic Epoxy Amercoat 90 Series Phenolic Epoxy Amercoat 90 Series Phenolic Epoxy	SSPC-SP10 (Sa 2 1/2)	125 - 150 stripe coat 125 - 150 250 - 300	5 - 6 5 - 6 10 - 12
T-27		Amercoat 351 100% Solids Epoxy Amercoat 351 100% Solids Epoxy Amercoat 351 100% Solids Epoxy	SSPC-SP10 (Sa 2 1/2)	200 - 300 stripe coat 200 - 300 400 - 600	8 - 12 8 - 12 16 - 24
T-28		Amercoat 91 Epoxy Novolac Amercoat 91 Epoxy Novolac Amercoat 91 Epoxy Novolac	SSPC-SP10 (Sa 2 1/2)	125 - 150 stripe coat 125 - 150 250 - 300	5 - 6 5 - 6 10 - 12
T-29		Amercoat 253 Epoxy Novolac Amercoat 253 Epoxy Novolac Amercoat 253 Epoxy Novolac	SSPC-SP10 (Sa 2 1/2)	125 - 150 stripe coat 125 - 150 250 - 300	5 - 6 5 - 6 10 - 12
T-30		Dimetcote 9 Series Inorganic Zinc	SSPC-SP10 (Sa 2 1/2)	75 - 100	3 - 4
T-31		Amercoat 240 Epoxy Series Amercoat 240 Epoxy Series	SSPC-SP10 (Sa 2 1/2)	150 - 200 150 - 200 300 - 400	6 - 8 6 - 8 12 - 16
FIREPROOFING					
F-33	Hydrocarbon fires [UL 1709 qualification]	Pitt-Char Epoxy Intumescent	Consult PPG Tech Service for system design.		
F-34	Cellulose fires [UL 263 qualification]	Steelguard FM Thin-film Intumescent	Consult PPG Tech Service for system design.		
Notes:	(1) The above schemes are offered as a guide to product selection for optimum performance. Exact recommendations and information regarding specific product characteristics, health and safety concerns, and other variations of these typical schemes to suit local conditions will be provided by local PPG representatives.				