



System Reference	Area	Coating System	Surface Preparation	Typical Dry Film Thickness	
				Microns	Mils
III Interior Surfaces					
L-1	Interior surfaces (machinery spaces, control room, storage areas, bulkheads, ceilings, etc.)	Dimetcote 9 Series Inorganic Zinc Coating	SSPC-SP 10 (Sa 2 1/2)	75 - 100	3 - 4
		Amercoat 385 Multi-purpose Epoxy Coating		125 - 150	5 - 6
		Amercoat 450 Series Aliphatic Polyurethane		50 - 75	2 - 3
				250 - 325	10 - 13
L-2		Amerlock Series High-solids Epoxy Coating	SSPC-SP 10 (Sa 2 1/2)	125 - 175	5 - 7
		Amerlock Series High-solids Epoxy Coating		125 - 175	5 - 7
L-3		Amercoat 240 Universal Epoxy	SSPC-SP 10 (Sa 2 1/2)	125 - 175	5 - 7
		Amercoat 240 Universal Epoxy		125 - 175	5 - 7
M-1	Living quarters (under insulation or uninsulated)	Dimetcote 9 Series Inorganic Zinc Coating	SSPC-SP 10 (Sa 2 1/2)	75 - 100	3 - 4
		Amercoat 385 Multi-purpose Epoxy Coating ²		125 - 150	5 - 6
M-2		Amerlock Series High-solids Epoxy Coating	SSPC-SP 10 (Sa 2 1/2)	100 - 125	4 - 5
		Amerlock Series High-solids Epoxy Coating		100 - 125	4 - 5
M-3		Amercoat 240 Universal Epoxy	SSPC-SP 10 (Sa 2 1/2)	100 - 125	4 - 5
		Amercoat 240 Universal Epoxy		100 - 125	4 - 5
N-1	Decks (interior walking surfaces in machinery spaces)	Amerlock Series High-solids Epoxy Coating Amerlock Glass Flake Epoxy Series (with Amercoat 888 Anti-slip Additive)	SSPC-SP 10 (Sa 2 1/2)	100 - 150 250 - 300 350 - 450	4 - 6 8 - 12 12 - 18
IV Tanks					
O-1 (USA)	Potable water tanks	Amercoat 240 Universal Epoxy ²	SSPC-SP 10 (Sa 2 1/2)	125 - 175	5 - 7
		Amercoat 240 Universal Epoxy stripe		125 - 175	5 - 7
		Amercoat 240 Universal Epoxy		250 - 350	10 - 14
O-2 (Europe)		Amercoat 351 100% Solids Epoxy	SSPC-SP 10 (Sa 2 1/2)	300	12
P-1	Storage tanks (fuel tanks, etc.)	Amercoat 90 Series Phenolic Epoxy	SSPC-SP 10 (Sa 2 1/2)	125 - 150	5 - 6
		Amercoat 90 Series Phenolic Epoxy		2 x stripe	2 x stripe
		Amercoat 90 Series Phenolic Epoxy		125 - 150	5 - 6
				250 - 300	10 - 12
P-2		Amercoat 253 High-solids Epoxy Novolac	SSPC-SP 10 (Sa 2 1/2)	125 - 150	5 - 6
		Amercoat 253 High-solids Epoxy Novolac		2 x stripe	2 x stripe
		Amercoat 253 High-solids Epoxy Novolac		125 - 150	5 - 6
				250 - 300	10 - 12
Q-1	Methanol tanks	Dimetcote 9 Series Inorganic Zinc Coating	SSPC-SP 10 (Sa 2 1/2)	75 - 100	3 - 4
Notes:	(1) The information contained herein is a guide for illustrative purposes only. Since individual project details will vary, please consult your local PPG representative for a detailed, project-specific coating specification (2) Coating certification depends on tank size. Contact PPG Technical Service for specific requirements.				