



**Global System Guide**

System Reference	Area	Coating System	Surface Preparation	Typical Dry Film Thickness	
				Microns	Mils
<b>I Exterior Surfaces (Page 1 of 2)</b>					
<b>A-1</b>	Jack-up Legs (from 0m level to top of legs)	Amercoat 385 Multi-purpose Epoxy Coating	SSPC-SP 10 (Sa 2 1/2)	100 - 125	4 - 5
		Amercoat 385 Multi-purpose Epoxy Coating		100 - 125	4 - 5
		Amercoat 385 Multi-purpose Epoxy Coating		100 - 125	4 - 5
				300 - 375	12 - 15
<b>A-2</b>		Amercoat 240 Universal Epoxy	SSPC-SP 10 (Sa 2 1/2)	150 - 200	6 - 8
		Amercoat 240 Universal Epoxy		150 - 200	6 - 8
				300 - 400	12 - 16
<b>B-1</b>	Bottom Hull (non-immersion except when in transit)	Dimetcote 9 Series Inorganic Zinc Coating	SSPC-SP 10 (Sa 2 1/2)	75 - 100	3 - 4
		Amercoat 385 Multi-purpose Epoxy Coating		100 - 150	4 - 6
		PSX 700 Series Engineered Siloxane		100 - 150	4 - 6
				275 - 400	11 - 16
<b>C-1</b>	Exposed surfaces, below 225F (hull sides, living quarters, drill floor areas, bulkheads, heliport undersides, piping, vessels, cranes, substructure and secondary steel, etc.)	Dimetcote 9 Series Inorganic Zinc Coating	SSPC-SP 10 (Sa 2 1/2)	75 - 100	3 - 4
		Amercoat 385 Multi-purpose Epoxy Coating		stripe	stripe
		PSX 700 Series Engineered Siloxane		125 - 175	5 - 7
				200 - 275	8 - 11
<b>C-2</b>		Dimetcote 9 Series Inorganic Zinc Coating	SSPC-SP 10 (Sa 2 1/2)	75 - 100	3 - 4
		Amercoat 385 Multi-purpose Epoxy Coating		125 - 150	5 - 6
		Amercoat 450 Series Aliphatic Polyurethane		50 - 75	2 - 3
				300 - 375	12 - 15
<b>C-3</b>		Amercoat 68 Series Zinc-rich Epoxy Primer	SSPC-SP 10 (Sa 2 1/2)	75 - 100	3 - 4
		Amerlock Series High-solids Epoxy Coating		stripe	stripe
		PSX 700 Engineered Siloxane Coating		125 - 150	5 - 6
				200 - 250	8 - 10
<b>C-4</b>		Amercoat 68 Series Zinc-rich Epoxy Primer	SSPC-SP 10 (Sa 2 1/2)	75 - 100	3 - 4
		Amercoat 240 Universal Epoxy		125 - 150	5 - 6
		Amercoat 450 Series Aliphatic Polyurethane		50 - 75	2 - 3
				250 - 325	10 - 13
<b>C-5</b>		Amercoat 68 Series Zinc-rich Epoxy Primer	SSPC-SP 10 (Sa 2 1/2)	75 - 100	3 - 4
		Amercoat 385 Multi-purpose Epoxy Coating		125 - 150	5 - 6
		Amercoat 450 Series Aliphatic Polyurethane		50 - 75	2 - 3
				250 - 325	10 - 13
<b>D-1</b>	Deck Surfaces (main deck, helideck)	Epok Screed	SSPC-SP 10 (Sa 2 1/2)	NA	NA
		Epok Tread Tiles (high profile)			
<b>D-2</b>		Amerlock Glass Flake Epoxy Series	SSPC-SP 10 (Sa 2 1/2)	400 - 500	16 - 20
		Amerlock Glass Flake Epoxy Series		400 - 500	16 - 20
		(with Amercoat 888 Anti-slip Additive)		800 - 1,000	32 - 40
<b>Notes:</b>	(1) The above schemes are offered as a guide to product selection for optimum performance. Exact recommendations and information regarding specific product characteristics, health and safety concerns, and other variations of these typical schemes to suit local conditions will be provided by local PPG representatives.				