

Thinners

General Information

The great majority of paints and coatings listed in this catalog were designed to be applied without thinning. There are circumstances, however, where some thinning is required, such as application during colder temperatures or with certain types of application equipment. Each Product Data Sheet lists the correct thinner and the limits of thinning. PPG cannot accept any responsibility or the use of unauthorized thinners.

Listed below are the thinners supplied by PPG, their product numbers and flash points. In addition, there is also a list of paints which utilize each thinner. This listing is only a guide. The Product Data Sheet must be consulted before thinning any PPG product.

It should be noted that some products in our line do not require thinning for application, but may require a thinner for clean-up. This information can be found on the Product Data Sheets.

Product	Description	Flash Point (US*)	Flash Point (Europe*)
T-10	Thinner	80°F (27°C)	25°C (77°F)
Amercoat 8	Thinner	20°F (-7°C)	
Amercoat 9HF	Thinner/Cleaner		26°C (79°F)
Amercoat 12	Cleaner, SCAQMD Rule 1171	2°F (-17°C)	24°C (75°F)
Amercoat 13	Thinner/Cleaner		12°C (54°F)
Amercoat 15	Thinner/Cleaner	106°F (41°C)	41°C (106°F)
Amercoat 65	Thinner	78°F (26°C)	24°C (75°F)
Amercoat 101	Thinner	145°F (63°C)	
Amercoat 104	Water-based Cleaner	230°F (110°C)	
Amercoat 900	Thinner		-5°C (23°F)
Amercoat 902	Thinner		43°C (109°F)
Amercoat 903	Thinner		78°C (172°F)
Amercoat 911	Thinner	76°F (24°C)	27°C (81°F)
Amercoat 920	Thinner		42°C (108°F)
Amercoat 923	Thinner	102°F (39°C)	
Amercoat 924	Thinner	140°F (60°C)	
Amercoat 927	Thinner	60°F (16°C)	
Amercoat 930	Thinner	214°F (101°C)	101°C (214°F)

* Due to differences in legislation for different areas, minor differences in composition may result in other flashpoints.